

SILPRO

SKIM PRO

Delivers a True Featheredge
No Priming Necessary
One Component — Mix with Water
Easy Mixing
Effortless Application

SILPRO LLC / 2 NEW ENGLAND WAY / AYER, MA 01432-1514 / 800-343-1501 / 978-772-4444 / FAX 978-772-7456 / WWW.SILPRO.COM



Silpro Skim Pro Skim Coat is a high performance, one component product for leveling and smoothing concrete, ceramic and quarry tile, terrazzo, wood, and water-insoluble cut-back adhesive prior to the installation of finished flooring like VCT, continuous vinyl flooring, or other standard flooring products. This Portland cement-based product mixes easily with water to produce a skim coat that is exceptionally easy to apply, does not require priming, and cures sufficiently for flooring installation in as little as 30 minutes, depending on thickness and drying conditions.

ADVANTAGES

- Delivers a true featheredge
- No priming necessary
- Mix with water
- Easy mixing
- Effortless application
- High coverage rate
- Excellent adhesion to concrete, plywood, and ceramic tile
- Long working time, 15 – 20 minutes
- Fast curing — flooring installed in as little as 30 minutes, foot traffic in 3 – 5 hours
- High bond and compressive strength

ADVANTAGES (CONT.)

- Can be used over all common flooring bases: concrete, wood, tile, etc.
- Can be built up to 1/2 inch and fill floor depressions, gouges, or spalls
- Is compatible with all floor covering adhesives

TECHNICAL DATA

Working Time at 70°F.	15 – 20 minutes
Final Set at 70°F.	30 – 50 minutes

SURFACE PREPARATION

Concrete: All surfaces must be completely cured, clean, and free of any loose or friable material. All bond-inhibiting materials such as paint, oil, curing compounds, waxes, sealers, gypsum, or any other material that may inhibit bonding shall be removed by shotblasting or other mechanical means. Cut-back or residual adhesive should be removed to a minimum using the techniques recommended by the Resilient Floor Covering Institute.

Skim Pro can be used over residual water-insoluble adhesive and cut-back that does not contain ingredients that could migrate and cause bond failure. The moisture content of the finished surface shall comply with adhesive and floor covering manufacturers' recommendations.

For Customer Service, Call Silpro at 1-800-343-1501

SURFACE PREPARATION (CONT.)

Wood: Surfaces must be free of any bond-inhibiting material such as wax, oil, paint, etc.

Cement Terrazzo, Ceramic Tile: All waxes, sealers, and any bond-inhibiting materials must be removed prior to applying **Skim Pro**.

MIXING

The recommended mixing ratio is one part water : two parts powder by volume. This is equivalent to 2.5 quarts of water for an entire bag of 10 pounds of dry product.

Mix-water temperature will significantly alter working time and therefore ambient water temperature is recommended. Do not mix more material than can be used in 15 to 30 minutes.

Slight adjustment of water content to optimize troweling is acceptable, however, caution is advised because over-watering will reduce product strength and increase drying time.

Add water to a suitable container and add the powder while mixing by hand or mechanical means to obtain a lump-free consistency. When hand mixing, stir vigorously to achieve a creamy, lump-free consistency in seconds. Drill mix at low speed, continually moving the paddle through the material.

APPLICATION

Apply **Skim Pro** immediately after mixing with a steel trowel using sufficient pressure to fill defects and voids, create a smooth, flat surface, and featheredge the product to the sub floor. The product can be built up to 1/2 inch to fill deeper depressions, contained areas, and transitions. All control and expansion joints must be carried through. Do not bridge them as they may crack later.

All flooring adhesives that adhere to concrete will bond to **Skim Pro**. Working time is 15 to 20 minutes and may be extended by re-mixing. Do not add additional water as that will weaken the product and extend drying time.

Clean-up: Clean tools with water after use.

WAITING TIMES BEFORE COVERING

Floor coverings such as VCT, sheet vinyl, and carpet may be installed as soon as **Skim Pro** has sufficient strength for adhesive application. Depending on thickness and drying conditions, this could take as little as 30 minutes. Longer periods will be required for thick applications, cool substrates, or poor drying conditions.

Moisture-sensitive adhesives and flooring (wood, parquet, etc.) can be applied after 16 hours. It is important to insure that the moisture content of the substrate meets the flooring and adhesive manufacturers' specifications prior to installing these materials.

LIMITATIONS

- For interior application only
- Do not apply over metal, pressed board, or water-sensitive materials
- Do not use below 50°F
- Do not use in areas subject to standing water or continuous moisture exposure
- Insure that the finished sub floor meets all flooring and adhesive manufacturers' specifications

PACKAGE SIZE

10 lb bag

COVERAGE — SKIM COAT

Over Concrete: 100 – 150 square feet

Over Plywood: 200 – 250 square feet

SHELF LIFE

2 years

CAUTION!

SILPRO offers products that may contain cement, latex, epoxy, and other chemicals. Please review the Safety Data Sheet before the use of this product.

GUARANTEE

Silpro LLC guarantees that their products are made of the finest raw materials under exacting care to produce products of the highest quality and will perform as stated when used in accordance with the manufacturer's printed instructions.

Improper mixing, incorrect application or other factors beyond the control of the manufacturer may produce unsatisfactory results and can not be held to be the manufacturer's responsibility. Silpro accepts no responsibility beyond the purchase price of the Silpro product used.

For further product information on **Skim Pro** consult your local dealer or call Silpro LLC at: **800-343-1501, 978-772-4444, FAX 978-772-7456.**

SILPRO